

Roltec SF

Produktfakta og anvendelsesområder

Uddeholm A/S
Kokmose 8 · 6000 Kolding
Tlf.: 75 51 70 66 · Fax: 75 51 70 44
www.uddeholm.dk
e-mail: info@uddeholm.dk



Critical tool steel properties for

GOOD TOOL PERFORMANCE

- Correct hardness for the application
- High wear resistance
- Good toughness to prevent cracking
- Good ductility to prevent chipping

High wear resistance is often associated with low toughness and ductility and vice-versa. However, in many cases high wear resistance and resistance to chipping or cracking are essential for optimal tool performance.

Roltec is a spray formed* cold work tool steel offering a combination of high wear resistance and very good resistance to chipping and cracking.

TOOLMAKING

- Machinability
- Grindability
- Heat treatment
- Dimensional stability in heat treatment
- Surface treatment

Roltec has a high wear resistance and this means that it is particularly important to use suitable cutting tools and cutting conditions. Similarly, suitable grinding wheels and grinding conditions should be used.

Due to the carefully balanced alloying Roltec has a similar heat treatment procedure to the steel AISI D2. One big advantage with Roltec is that the dimensional stability after hardening is better than for conventionally produced high alloyed cold work steels.

Applications

Roltec is suitable for medium and long run tooling where the work materials used are likely to result in mixed or abrasive wear and/or chipping/cracking and/or plastic deformation of the tool.

Examples:

- Cold rolls requiring high wear resistance and resistance to cracking
- Form rolls requiring a high wear resistance and resistance to cracking
- Knives
- Engineering applications
- Substrate for surface coating

* Roltec is spray formed by Dan Spray A/S

General

Roltec is a chromium-molybdenum-vanadium alloyed cold work tool steel which is characterized by:

- High wear resistance
- High compressive strength
- High toughness
- Good dimensional stability at heat treatment and in service
- Very good through-hardening properties
- Very good resistance to tempering back
- Good WEDM properties
- Good surface treatment properties.

Typical analysis %	C 1,4	Si 1,0	Mn 0,6	Cr 4,6	Mo 3,2	V 3,7
Standard specification	None					
Delivery condition	Soft annealed to approx. 240 HB					
Colour code	Blue/green					

Properties

PHYSICAL DATA

Hardened and tempered to 62 HRC

Temperature	20°C (70°F)	200°C (390°F)	400°C (750°F)
Density kg/m ³ lbs/in ³	7 650 0,276	– –	– –
Modulus of elasticity MPa psi	215 000 31,2 x 10 ⁶	196 000 28,4 x 10 ⁶	185 000 26,8 x 10 ⁶
Coefficient of thermal expansion per °C from 20°C °F from 68°F	– –	11,4 x 10 ⁻⁶ 6,3 x 10 ⁻⁶	12,1 x 10 ⁻⁶ 6,7 x 10 ⁻⁶
Thermal conductivity W/m°C Btu in (ft ² h°F)	– –	25 174	27 188
Specific heat J/kg °C Btu /lb °F	460 0,11	– –	– –

COMPRESSIVE STRENGTH



Hardness HRC	Compressive strength Rc0,2 (MPa)
50	1 550
55	2 100
60	2 550
62	2 750
64	2 950

IMPACT STRENGTH


Approximate room temperature impact strength at different tempering temperatures.

Specimen size: 7 x 10 x 55 mm (0,27 x 0,4 x 2,2") unnotched.

Hardened for 30 minutes, except at 1150°C (2100°F) where 10 minutes are used. Quenched in air. Tempered 2 x 2h.




Relative chipping resistance for AISI D2, Weartec, Roltec and PM 23 at 60 HRC. High value indicates good ductility. High temperature tempered condition.



WEAR RESISTANCE

Relative abrasive wear resistance for WEARTEC, Roltec, PM23 and AISI D2 at 60 HRC. A high value indicates good wear resistance. High temperature tempered condition.



Heat treatment recommendations

SOFT ANNEALING

Protect the steel and heat through to 900°C (1650°F). Then cool in the furnace at 10°C (20°F) per hour to 650°C (1200°F), then freely in air.

STRESS RELIEVING

After rough machining the tool should be heated through to 650°C (1200°F), holding time 2 hours. Cool slowly to 500°C (930°F), then freely in air.

HARDENING

Preheating in two stages: 600–650°C (1100–1200°F) and 900–950°C (1650–1740°F)

Austenitizing temperature: 950–1150°C (1740–2100°F), normally 1020°C (1870°F).

Holding time: 30 min. for ≤1120°C (2050°F), 10 minutes for >1120°C (2050°F).

Protect the part against decarburization and oxidation during hardening.


QUENCHING MEDIA

- High speed gas/circulating atmosphere
- Vacuum furnace (high speed gas with sufficient overpressure)
- Martempering bath or fluidized bed at 500–550°C (930–1020°F)
- Martempering bath or fluidized bed at approx. 200–350°C (390–660°F)

Note: Temper the tool as soon as its temperature reaches 50–70°C (120–160°F).


CCT-graph

Austenitizing temperature 1025°C (1875°F). Holding time 30 minutes.




TTT-graph

Austenitizing temperature 1025°C (1875°F). Holding time 30 minutes.



Hardness and retained austenite as a function of austenitizing temperature.

10 minutes holding time at 1150°C (2100°F), else 30 minutes.





TEMPERING

Choose the tempering temperature according to the hardness required by reference to the tempering graphs below.

Temper at least twice with intermediate cooling to room temperature. The lowest tempering temperature which should be used without deep cooling is 525°C (980°F) and with sub-zero treatment 500°C (930°F). The minimum holding time at temperature is 2 hours. For a hardening temperature of ≥1100°C (2010°F) Roltec should be sub-zero cooled and/or high temperature tempered three times in order to reduce the amount of retained austenite.

Tempering graphs without sub-zero treatment after hardening



SUB-ZERO TREATMENT

Pieces requiring maximum dimensional stability in service can be sub-zero treated as follows:

Immediately after quenching the piece should be sub-zero treated to -70 to -80°C (-95 to -110°F), soaking time 1–3 hours, followed by tempering. Sub-zero treatment will give a hardness increase of ~ 1 HRC. Avoid intricate shapes as there will be risk of cracking.

For the highest demands on dimensional stability, sub-zero cooling in liquid nitrogen is recommended after quenching and after each tempering.

DIMENSIONAL CHANGES


The dimensional changes have been measured after austenitizing and tempering.

Austenitizing: 1025°C (1875°F)/30 min, cooling in vacuum furnace at $1,1^{\circ}\text{C/s}$ ($1,8^{\circ}\text{F/s}$) between 800°C (1470°F) and 500°C (930°F)

Tempering: 2 x 2 h at various temperatures

Specimen size: 100 x 100 x 100 mm (3,9 x 3,9 x 3,9")

Dimensional changes in length, width and thickness after hardening and tempering



Surface treatments

Some cold work tool steels are given a surface treatment in order to reduce friction and increase wear resistance. The most commonly used treatments are nitriding and surface coating with wear resistant layers produced via PVD or CVD.

The high hardness and toughness together with a good dimensional stability makes Roltec ideal as a substrate steel for various surface coatings.

NITRIDING

Nitriding gives a hard surface layer that is resistant to wear and erosion.

Roltec is normally high temperature tempered at 525°C (980°F). This means that the nitriding temperature used should not exceed 500 – 525°C (930 – 980°F). Ion nitriding at a temperature below the tempering temperature used is preferred.

The surface hardness after nitriding is approximately $1150 \text{HV}_{0,2\text{kg}}$. The thickness of the layer should be chosen to suit the application in question.

Process	Time	Depth	
		mm	inch
Gas nitriding at 510°C (950°F)	10 h	0,15	0,0059
Plasma nitriding at 480°C (895°F)	10 h	0,10	0,0039
	30 h	0,20	0,0079

PVD

Physical vapour deposition, PVD, is a method of applying a wear resistant coating at temperatures between 200 – 500°C (390 – 930°F).


CVD

Chemical vapour deposition, CVD, is used for applying wear resistant surface coatings at a temperature approx. 1000°C (1830°F). It is recommended that the tools should be separately hardened and tempered in vacuum furnace after surface treatment.

Machinability

Relative machinability and grindability for Weartec, Roltec, AISI D2 and PM 23. A high value indicates good machinability/grindability.

Relative machinability/
grindability



Machining recommendations

The cutting data below are to be considered as guide values which must be adapted to existing local conditions.

Condition: Soft annealed to approx. 240 HB

TURNING

Cutting data parameters	Turning with carbide	
	Rough turning	Fine turning
Cutting speed, v_c m/min. f.p.m.	100–150 330–500	150–200 500–800
Feed, f mm/rev. i.p.r.	0,2–0,4 0,008–0,016	0,05–0,2 0,002–0,008
Depth of cut, a_p mm inch	2–4 0,08–0,16	0,5–2 0,02–0,08
Carbide designation ISO	K20*, P20	K15, P15

* Use a wear resistant Al_2O_3 -coated carbide

DRILLING

High speed steel twist drill

Drill diameter		Cutting speed v_c		Feed f	
mm	inch	m/min.	f.p.m.	mm/r	i.p.r.
– 5	–3/16	10–12*	33–40*	0,05–0,10	0,002–0,004
5–10	3/16–3/8	10–12*	33–40*	0,10–0,20	0,004–0,008
10–15	3/8–5/8	10–12*	33–40*	0,20–0,25	0,008–0,010
15–20	5/8–3/4	10–12*	33–40*	0,25–0,30	0,010–0,012

* For coated HSS drill v_c 20–25 m/min. (66–83 f.p.m.)

Carbide drill

Cutting data parameters	Type of drill		
	Indexable insert	Solid carbide	Brazed carbide ¹⁾
Cutting speed, v_c m/min. f.p.m.	100–130 330–430	50–60 165–200	30–40 100–130
Feed, f mm/r i.p.r.	0,05–0,15 ²⁾ 0,002–0,006 ²⁾	0,10–0,25 ²⁾ 0,004–0,010 ²⁾	0,15–0,25 ²⁾ 0,006–0,010 ²⁾

¹⁾ Drill with internal cooling channels and brazed tip.

²⁾ Depending on drill diameter.

MILLING

Face and square shoulder milling

Cutting data parameters	Milling with carbide	
	Rough milling	Fine milling
Cutting speed, v_c m/min. f.p.m.	90–100 300–330	100–120 330–400
Feed, (f_z) mm/tooth inch/tooth	0,2–0,4 0,008–0,016	0,1–0,2 0,003–0,008
Depth of cut, a_p mm inch	2–4 0,08–0,16	–2 –0,08
Carbide designation ISO	K20–P20 Coated carbide*	K15–P15 Coated carbide*

* Use a wear resistant Al_2O_3 -coated carbide

End milling

Cutting data parameters	Type of mill		
	Solid carbide	Carbide indexable insert	High speed steel ¹⁾
Cutting speed, v_c m/min. f.p.m.	40–50 130–165	80–110 260–360	5–8 17–26
Feed, f_z mm/tooth inch/tooth	0,03–0,2 ²⁾ 0,001–0,008 ²⁾	0,08–0,2 ²⁾ 0,003–0,008 ²⁾	0,05–0,35 ²⁾ 0,002–0,014 ²⁾
Carbide designation ISO	–	K15 ³⁾	–

¹⁾ With coated HSS v_c =14–18 m/min. (40–60 f.p.m.)

²⁾ Depending on radial depth of cut and cutter diameter.

³⁾ Use a wear resistant Al_2O_3 -coated carbide

BAND SAWING

For sawing of Roltec use a band with a coarse tooth pitch, but at least three teeth must be engaged in the workpiece at the same time.

	HSS bi-metal band	Carbide tipped band
Cutting speed m/min. f.p.m.	20–25 65–80	60–70 200–230
Down feed mm/min. inch/min.	6–8 0,2–0,3	20–22 0,8–0,9

GRINDING

General grinding wheel recommendations are given below. More information can be found in the Uddeholm publication "Grinding of Tool Steel".

Type of grinding	Annealed condition	Hardened condition
Face grinding straight wheel	B151 R50 B3 ¹⁾ A 46 HV ²⁾	B151 R50 B3 ¹⁾ A 46 GV ²⁾
Face grinding segments	A 36 GV	A 46 GV
Cylindrical grinding	B151 R50 B3 ¹⁾ A 60 KV ²⁾	B151 R50 B3 ¹⁾ A 60 JV ²⁾
Internal grinding	B151 R75 B3 ¹⁾ A 60 JV	B151 R75 B3 ¹⁾ A 60 IV
Profile grinding	B126 R100 B6 ¹⁾ A 100 JV ²⁾	B126 R100 B6 ¹⁾ A 100 IV ²⁾

¹⁾ The first choice is a CBN-wheel for this operation

²⁾ Preferable a wheel type containing sintered Al₂O₃ (seeded gel)

Electrical-discharge machining, EDM

If EDM is performed in the hardened and tempered condition, finish with "fine-sparking", i.e. low current, high frequency.

For optimal performance the EDM'd surface should be ground/polished and the tool retempered at approx. 25°C (50°F) lower than the original tempering temperature.

When EDM'ing larger sizes or complicated shapes Roltec should be tempered at high temperatures, ≥525°C (980°F).

Further information

Please, contact your local Uddeholm office of further information on the selection, heat treatment, application and availability of Uddeholm tool steels.

Relative comparison of Uddeholm cold work tool steels

MATERIAL PROPERTIES AND RESISTANCE TO FAILURE MECHANISMS

Uddeholm grade	Hardness/ Resistance to plastic deformation	Machinability	Grindability	Dimension stability	Resistance to		Fatigue cracking resistance	
					Abrasive wear	Adhesive wear	Ductility/ resistance to chipping	Toughness/ gross cracking
ROLTEC	██████	██	██	██████	██████	██	██	██
WEARTEC	██████	██	██	██████	██████████	██	██	██
AISI D2	████	████	████	████	██	██	██	██
PM 23	██████	██████	██████	██████	██	██████	██████	██████